

## GOLD STAR BRASSCAST

Gold Star BrassCast is an exceptionally competitive, plaster-bonded investment powder, specifically formulated by optimizing the particle-size distribution and thermal expansion to help casters to compete in the most demanding of environments.



Gold Star Powders Private Limited No.112/2,Chinna Amman Koil Street, Kalavakkam Village, Thiruporur - 603 110, Tamil Nadu Tel +91 44 4743 9999 Email info@goldstarpowders.in



## GOLD STAR BRASSCAST


Do not remove flasks from furnace to cast until they have been held at casting temperature for a minimum of 1 hour. If held for less than 1 hour, the core of the flasks will be at a much higher temperature than the digital temperature display states, and may result in metal mould reaction.

- Do no not cast with a flask temperature lower than 650°C
- Slurry temperature 21°C
- · Leave for 90 min to stand before burnout

WATER TO POWDER RATIO	
MACHINE VACUUM MIXING	38:100
HAND MIX THEN VACUUM	40:100

MACHINE VACUUM MIXING	Min.
Weigh out water and powder	0
Add powder to water	0
Mix under vacuum	1
Stop mixer and scrape blades	0.5
Mix under va cuum	3.5
Pour flasks	2
Vacuum flasks	1
Total time take	8

HAND MIX THEN VACUUM	Min.
Weigh out water and powder	0
Add powder to water	0
Mix by hand	1
Mix with machine	3
Vacuum mixer bowl	1
Pour flasks	1
Vacuum flasks	2
Total time taken	8



Gold Star Powders Private Limited
No.112/2, Chinna Amman Koil Street, Kalavakkam Village, Thiruporur - 603 110, Tamil Nadu
Tel +91 44 4743 9999 Email info@goldstarpowders.in